

UNCLASSIFIED

AD 295 804

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA




UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

62-1539

295804



PROPERTIES OF BLENDED BARIUM AND
STRONTIUM FERRITES

By

Ye. S. Borovik and N. G. Usikova

295 804

UNEDITED ROUGH DRAFT TRANSLATION

PROPERTIES OF BLENDED BARIUM AND STRONTIUM FERRITES

By: Ye. S. Borovik and N. G. Usikova

English Pages: 9

Source: Fizika Metallov i Metallovedenie, Vol. 13,
No. 3, 1962, pp. 470-474.

SC-1589
SOV/126-62-13-3-22/23

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION SERVICES BRANCH
FOREIGN TECHNOLOGY DIVISION
WP-AFB, OHIO.

FTD-TT-62-1539/1+2+4

Date 4 Jan. 19 63

PROPERTIES OF BLENDED BARIUM AND STRONTIUM FERRITES

Ye. S. Borovik and N. G. Usikova

Barium and strontium ferrites belong to the hard ferromagnetic materials. But in comparison with the magnetic alloy magnico these ferrites possess lowered residual inductance B_r and less magnetic energy $(BH)_{\max}$, although they do have increased coercive force H_c .

In the literature there are data on increasing magnetic energy in hard ferrites by additives of various oxides [1-3]. In this work the same aim of increasing the magnetic energy of ferrites is pursued and the results of research on the magnetic properties and several physical properties of blended hard ferrites of composition $Ba_{1-x}Sr_xO \cdot 6Fe_2O_3$ are presented.

Specimen Preparation and Measurement Technique

To prepare specimens of composition $Ba_{1-x}Sr_xO \cdot Fe_2O_3$ weight ratios of the powders $BaCO_3$, $SrCO_3$, and Fe_2O_3 were taken corresponding to the needed composition. The powder mixture (in the form of a liquid mass with water) was carefully ground for several hours in a mortar. Then the mixture was dried and roasted for five hours at $1100^\circ C$ to form the blended ferrite. The slightly sintered ferrite powder was

ground in the mortar and from it were pressed specimens at a pressure of about 17 t/cm² without any binding material. The pressed intermediate products were sintered for an hour. Preliminary research showed that the optimum sintering regime lay between 1200-1300°. The specimens were 1 cm long cylinders with a cross-section of about 0.18 cm². The magnetic properties of the specimens were measured by the bridge method in fields up to 7000 oe at room temperature.

Results of Measurement

Figure 1 shows the dependence of the maximum magnetic energy $(BH)_{\max}$ on composition for different sintering temperatures (curves 1-4). For a 1200° sintering temperature (curve 1) the magnetic properties of the blended ferrites turn out to be poorer than in pure ferrites. The curve $(BH)_{\max}$ as a function of the composition has a minimum for the ferrite Ba_{0.5}Sr_{0.5}O · 6Fe₂O₃. At this sintering temperature the size of the blended ferrite particles has evidently not yet attained the maximum size of single-domain particles.

For other sintering temperatures the properties of some blended ferrites are found to be better than in pure barium and strontium ferrites. It is evident from Fig. 1 that the curve of the dependence of $(BH)_{\max}$ on composition has a maximum for Ba_{0.7}Sr_{0.3}O · 6Fe₂O₃. The ferrite Ba_{0.25}Sr_{0.75}O · 6Fe₂O₃ has poorer magnetic properties. The magnitude of the maximum magnetic energy $(BH)_{\max}$ in Ba_{0.7}Sr_{0.3}O · 6Fe₂O₃ specimens at sintering temperature 1230° attains a value of $1.45 \cdot 10^6$ gs · oe, i.e., almost 70% more than in pure barium ferrite and almost 50% more than in pure strontium ferrite. In sintering the specimens at 1300° the nature of the curve changes: the maximum on the curve of magnetic energy is displaced to ferrite Ba_{0.5}Sr_{0.5}O · 6Fe₂O₃, but

this maximum is already substantially less pronounced and the absolute values of $(BH)_{\max}$ for this sintering temperature are less for all the compositions than at 1230° .

The same figure shows the dependence of the residual intensity of magnetization B_r (curve 5) and of the coercive force $I H_c$ (curve 6) on composition for the best sintering temperature 1230° . At this temperature the maximum B_r is observed in the same ferrite composition in which the minimum occurs on the curve of magnetic energy. A minimum is also observed for $Ba_{0.25}Sr_{0.75}O \cdot 6Fe_2O_3$, but the maximum and minimum on this curve are less sharply pronounced than on the magnetic energy curve.

The coercive force curve has one minimum for a composition of approximately $Ba_{0.5}Sr_{0.5}O \cdot 6Fe_2O_3$. Changes in the form of the curve of the dependence of B_r on composition connected with the sintering temperature are similar to changes for the curves of $(BH)_{\max}$. The shape of the dependence curve of $I H_c$ on composition is preserved unchanged for all the investigated sintering temperatures. The absolute values fall at sintering temperatures higher than 1200° .

The same curve nature was observed if the pure ferrites were sintered at optimum temperatures before preparing the blended ferrite and then the specimen of blended ferrite was obtained by re-sintering the pulverized and carefully mixed pure ferrite powders. The effects in this process were, however, much less clearly expressed.

To illustrate the temperature dependence of the investigated properties, Figure 2 shows the dependence curves of magnetic energy $(BH)_{\max}$ on sintering temperature for differing compositions (curves 1-4) and residual intensity of magnetization B_r (curves 5-7).

The curves of $(BH)_{\max}$ as a function of the sintering temperature

are in general similar for all compositions, but for a composition near the optimum ($\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$) the most clearly expressed maximum is at a sintering temperature near 1230° . The curves of B_r for this ferrite composition have the same nature of temperature dependence with a maximum near 1230° . The temperature dependence of B_r for pure ferrites and the ferrite corresponding to composition $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ are much less clearly expressed. The growth of B_r with the sintering temperature for ferrite $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ deserves attention.

The curves of demagnetization for pure barium and strontium ferrites and for blended ferrites with extreme values of the properties ($\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ and $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$) are shown in Fig. 3.

Table 1 lists the values of the basic magnetic parameters of pure barium and strontium ferrites and of blended ferrites on magnetization in a field up to 7000 oe for the optimum sintering regime. For comparison the best data in the literature for isotropic ferrites [4] and an example for one of the anisotropic specimens [5] are also listed.

As is evident from Table 1, the properties of the composition near the optimum one are better than the properties of an ordinary isotropic ferrite (the magnitude of $(BH)_{\max}$ is 75% greater and approaches the values of the anisotropic ferrite). The authors propose subsequently to investigate anisotropic blended ferrites.

Density and Physical Properties of the Specimens

An investigation of the results of measuring the properties of blended ferrites shows that in these specimens the physical properties also change. Figure 4 displays the curves of change of density of the

blended ferrites in relationship to sintering temperature. From a comparison of the curves it is evident that the $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ specimen sinters best of all and the $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ specimen, poorest of all, the sintering process finishing for the latter at 1230° and its density not changing at a subsequent increase in this temperature.

Table 2 lists the data on measuring microhardness and ultimate strength σ_{ult} during compression.




Fig. 1. Curves of the dependence of blended $\text{Ba}_{1-x}\text{Sr}_x\text{O} \cdot 6\text{Fe}_2\text{O}_3$ ferrites on composition for various sintering temperatures. $(\text{BH})_{\text{max}}$ at 1) 1200° ; 2) 1230° ; 3) 1260° ; 4) 1300°C ; 5) B_r at 1230°C ; 6) I_{H_c} at 1230°C .




Fig. 2. Dependence of the properties of blended ferrites on sintering temperature for various compositions. $(\text{BH})_{\text{max}}$ for 1) $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 2) $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 3) $\text{BaO} \cdot 6\text{Fe}_2\text{O}_3$; 4) $\text{SrO} \cdot 6\text{Fe}_2\text{O}_3$; B_r for 5) $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 6) $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 7) $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 8) $\text{BaO} \cdot 6\text{Fe}_2\text{O}_3$.

The ferrite with the optimum magnetic properties also has essentially the best physical properties, compared with pure ferrites. We may achieve an increase in the physical properties of pure ferrites by increasing the sintering temperature and using more active materials,

so that the listed figures for density and strength have only a relative significance. But for practical use it is essential that good physical properties be also found for composition $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ which has the best magnetic properties. It is curious to note very poor sinterability and low strength in $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ ferrite.

Discussion of the Results

In the blended ferrite system $\text{Ba}_{1-x}\text{Sr}_x\text{O} \cdot 6\text{Fe}_2\text{O}_3$ a non-monotonic relationship between properties and composition is observed. Ferrite of composition $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ at the optimum sintering temperature has better, and $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ ferrite worse, properties than the pure components. Evidently the former's good properties are essentially caused by the better sinterability of the specimen of this composition. To illustrate this, the relationship of magnetic properties to composition with a correction for porosity was drawn. All the results of measuring magnetization were reduced to the single density value of 4.8 g/cm^3 by the formula $I_{\text{corr}} = I \left(\frac{4.8}{\rho} \right)^{2/3}$. This method of introducing corrections is arbitrary to a certain degree, but since the theoretical density of the blended ferrites is not known to us we must confine ourselves to it.

Figure 5 shows the curves of $(\text{BH})_{\text{max}}$ and B_r reduced to a single density at the optimum sintering temperature 1230° . As may be seen, the curve maximum has substantially smoothed out and the minimum has become sharper. Thus, although the shape of the curves is partially caused by the different sinterabilities of the differently composed specimens, still some other causes evidently lie at the bottom of the observed relationships. Research on the physical properties of such systems will be continued later on, but right now it is already clear




Fig. 3. Demagnetization curves for ferrites of differing composition (sintering temperature 1230°C). 1) $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 2) $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 3) $\text{SrO} \cdot 6\text{Fe}_2\text{O}_3$; 4) $\text{BaO} \cdot 6\text{Fe}_2\text{O}_3$.




Fig. 4. Dependence of density ρ on sintering temperature in ferrites of differing composition. 1) $\text{SrO} \cdot 6\text{Fe}_2\text{O}_3$; 2) $\text{Ba}_{0.25}\text{Sr}_{0.75}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 3) $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{O} \cdot 6\text{Fe}_2\text{O}_3$; 4) $\text{Ba}_{0.75}\text{Sr}_{0.25}\text{O} \cdot 6\text{Fe}_2\text{O}_3$.




Fig. 5. Dependence of properties of blended $\text{Ba}_{1-x}\text{Sr}_x\text{O} \cdot 6\text{Fe}_2\text{O}_3$ ferrites on composition, adjusted to the practical density of barium ferrite, 4.8 g/cm³ (sintering temperature 1230°C). 1) $(\text{BH})_{\text{max}}$; 2) B_r .

TABLE 1

Composition	B_r , G	H_c , Oe	$(BH)_{\max} \times 10^{-6}$, G \cdot Oe	Density, g/cm ³	T_{int} , °C
BaO · 6Fe ₂ O ₃	1950	3750	0,84	3,02	1230
SrO · 6Fe ₂ O ₃	2050	4200	1	3,08	1230
Ba _{0,75} Sr _{0,25} O · 6Fe ₂ O ₃	2800	2700	1,45	4,5	1230
Ba _{0,25} Sr _{0,75} O · 6Fe ₂ O ₃	1900	3200	0,71	3,25	1260
BaO · 6Fe ₂ O ₃					
Isotropic	2050	2420	0,85	4,8	—
BaO · 6Fe ₂ O ₃					
Anisotropic	3000	1800	1,8	4,8	1300

TABLE 2

Composition	Microhardness No.	σ_{ult} , kg/cm ²
BaO · 6Fe ₂ O ₃	96,5	2000
SrO · 6Fe ₂ O ₃	106,3	1770
Ba _{0,25} Sr _{0,75} O · 6Fe ₂ O ₃	41,2	1770
Ba _{0,5} Sr _{0,5} O · 6Fe ₂ O ₃	885	2800
Ba _{0,75} Sr _{0,25} O · 6Fe ₂ O ₃	600	3500

that blended ferrite $\text{Ba}_{0.7}\text{Sr}_{0.3}\text{O} \cdot 6\text{Fe}_2\text{O}_3$ is a better magnetic material than pure barium and strontium ferrites.

In conclusion we thank Prof. B. Ya. Pines for valuable advice.

A. M. Gor'kiy, State University
of Khar'kov

Received May 3, 1961; in
corrected form, Sept. 12, 1961.

REFERENCES

1. G. H. Muller and G. Heimke. Ber. Arbeitsgemeinschaft Ferromagnetismus 1958, Stuttgart, Riederer, 1958.
2. L. Kozlowski and Z. Ziolkowski. Prace Inst. hutn., 10, No. 6, 1958.
3. Kojima Hiroshi. Sci. Rep. Res. Inst. Tohoku Univ., A10, No. 2, 1958.
4. G. A. Semenov and K. K. Ozols. Trudy NII MRTP, No. 5 (41), 1957.
5. L. Ya. Shchepkina. Scientific-Technological Collection, No. 3/5, MRTP, 1955.

DISTRIBUTION LIST

DEPARTMENT OF DEFENSE	Nr. Copies	MAJOR AIR COMMANDS	Nr. Copies
		AFSC	
		SCFTR	1
		ASTIA	25
HEADQUARTERS USAF		TD-B1a	5
		TD-B1b	3
AFPCIN-3D2	1	AEDC (AEY)	1
ARL (ARB)	1		
OTHER AGENCIES			
CIA	1		
NSA	6		
AID	2		
OPS	2		
AEC	2		
PWS	1		
NASA	1		
RAND	1		